



## **Architectural Specifications Guidelines**

### **Recycled Rubber Flooring Tiles – Indoor Applications**

#### **Fitness Tiles**

**Section 09 65 19**  
**Resilient Tile Flooring**

**Section 09 62 00**  
**Athletic Tile Flooring**

#### **Part 1 General**

##### **1.1 Section Includes**

- A. Resilient tile flooring and accessories.

##### **1.2 Related Sections**

- A. Section 03 30 00 - Cast-in-Place Concrete.
- B. Section 06 10 00 - Rough Carpentry.
- C. Section 07 26 00 - Vapor Retarders.
- D. Section 09 62 00 – Athletic Flooring
- E. Section 09 65 13 - Resilient Base and Accessories:

##### **1.3 References**

- A. ASTM International (ASTM) and others as noted:
  - 1. AATTC 134-06 Standard for Electrostatic Propensity of Carpets
  - 2. ASTM C423 Standard Test Method for Sound Absorption, Noise Reduction Coefficient
  - 3. ASTM C501 Standard Test Method for Relative Resistance to Wear of Rubber Tile by the Taber Abraser
  - 4. ASTM D2047 Standard Test Method for Coefficient of Friction of Polish-Coated Floor Surfaces as Measured by the James Machine
  - 5. ASTM D2240 Standard Test Method for Rubber Property-Durometer Hardness
  - 6. ASTM D3676 Standard Specification for Density Rubber Cellular Cushion Used for Carpet or Rug Underlay
  - 7. ASTM D395B Standard Test Methods for Rubber Property-Compression Set
  - 8. ASTM D412 Standard Test Methods for Vulcanized Rubber and Thermoplastic Rubbers and Thermoplastic Elastomers –Tension
  - 9. ASTM D5116 Standard Guide for Small-Scale Environmental Chamber Determinations of Organic Emissions from Indoor Materials/Products. (V.O.C.)
  - 10. ASTM E492 Standard Test Method for Impact Sound Transmission
  - 11. ASTM E648-97 Standard Test Method for Critical Radiant Flux of Floor-Covering Systems Using a Radiant Heat Energy Source
  - 12. ASTM F137-03 Standard Test Method for Flexibility of Resilient Flooring Materials with Cylindrical Mandrel Apparatus
  - 13. ASTM F150 Standard Test Method for Electrical Resistance of Conductive and Static Dissipative Resilient Flooring
  - 14. ASTM F1914-98 Standard Test Method for Short-Term Indentation and Residual Indentation of Resilient Floor Covering

15. ASTM F925-97 Standard Test Method for Resistance to Chemicals of Resilient Flooring
16. ASTM F970-87 Standard Test Method for Static Load Limit
17. ASTM G21 Standard Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi
18. Phillips Roll Chair Test Method for Numeric Rating of Surface Structure
19. Federal Standard 101B/NFPA 99 12-4.1.3.8 –Static Decay Test Method 4046
20. California Specification 01350 (CHPS Compliant for VOC Emissions) - -Emission tests are performed following California Dept. of Health Services Standard Practice for the Testing of Volatile Organic Emissions from Various Sources Using Small-Scale Environmental Chambers, CA/DHS/EHLRB/R-174, 07/15/04 ([http://www.cal-iaq.org/VOC/Section01350\\_7\\_15\\_2004\\_FINAL\\_PLUS\\_ADDENDUM-2004-01.pdf](http://www.cal-iaq.org/VOC/Section01350_7_15_2004_FINAL_PLUS_ADDENDUM-2004-01.pdf))

#### 1.4 Submittals

- A. Submit under provisions of Section 01 30 00 - Administrative Requirements
- B. Product Data: Provide detailed data on each product to be used including but not limited to the following information as applicable:
  1. Preparation instructions and recommendations.
  2. Storage and handling requirements and recommendations.
  3. Installation methods.
  4. Maintenance recommendations.
- C. Selection Samples: For each color specified two sets of each type and color of recycled rubber flooring indicating full range of color and pattern variation.
- D. Verification Samples: For each finish product specified, two 6" x 6" sets of each type and colors of recycled rubber flooring, indicating color and pattern of actual product, including variations, as proof of application compliance.
- E. Closeout Submittals: Submit three copies of the following:
  1. Maintenance and operation data includes - methods for maintaining installed products, and precautions against cleaning materials and methods detrimental to finishes and performance.
  2. Documentation of warranty specified herein.
- F. Flame Spread Certification: Submit manufacturer's certification that resilient flooring furnished for areas indicated to comply with required flame spread rating has been tested and meets or exceeds indicated or required standard.
- G. MSDS: Submit manufacturer's Material Safety Data Sheets for specified adhesives/sealers

#### 1.5 Quality Assurance

- A. Installer Qualifications: Minimum two years' experience and completed at least three projects of similar magnitude, material, and complexity. Upon request, provide project references including contact names and telephone numbers for three projects.
- B. Provide recycled rubber flooring products manufactured by a Canadian firm with a minimum of 30 years' experience in the fabrication of such products, and of types of equivalents to those specified.
- C. Provide recycled rubber flooring products that are FloorScore® certified under the criteria developed by the Resilient Floor Covering Institute (RFCI) and certified by Scientific Certification Systems (SCS), Inc.
- D. Provide products with a minimum of 10 Year Limited Manufacturer's Warranty

## 1.6 Delivery, Storage & Protection

- A. **Delivery:** Deliver materials in manufacturer's original, unopened, undamaged wrapping and/or containers with identification labels intact clearly marking thickness, percentage of speckle and shade of color(s).
- B. **Inspection:** Inspect all deliveries to ensure undamaged goods, and for accurate product type for thickness, edge type, color, and speckle. Contact manufacturer immediately if product is damaged or inconsistent with order specifications.
- C. **Storage and Protection:** Carefully handle all materials and store protected from exposure to harmful weather and at temperature conditions recommended by the manufacturer. Remove pallet banding if long term storage is required but leave other packaging intact until acclimation is to be started.
- D. Flooring material and adhesive (if required) shall be acclimated to the installation area for a minimum of 24 hours prior to installation. See manufacturer's installation guidelines for details on proper acclimation procedures. Longer acclimation may be required if product has been stored for extended time periods.

## 1.7 Project Conditions

- A. Environmental Requirements/Conditions: In accordance with manufacturer's recommendations. Areas to receive flooring shall be clean, level, dry, fully enclosed, weather tight with the permanent HVAC set at a uniform temperature of at least Maintain 68F/20C degrees and less than 85F/30C continuously prior to, during and after installation, but for not less than 48 hours prior to and during, and for not less than 48 hours after installation. The flooring material shall be conditioned in the same manner prior to installation.
- B. Close spaces to traffic during rubber flooring installation and for a period after installation as recommended in writing by the manufacturer.
- C. Install rubber flooring materials and accessories after all other finishing operations, including painting, have been completed.
- D. Where demountable partitions and other items are indicated for installation on top of sheet resilient flooring material, install flooring material before these items are to be installed.
- E. Concrete substrates should not exceed 80 percent RH and/or 5 lbs. X 24 hrs. X 1000 sf. moisture vapor emissions rate tested in accordance with ASTM F 2170 and ASTM F 1869.

## 1.8 Warranty

- A. Warranty Period: Manufacturer's standard 5 Year Warranty against manufacturing defects.

## 1.9 Extra Materials

- A. Deliver to owner extra material of each tile type and color in the same manufactured lot, in quantities not less than 5% of total area installed for each product. Delivery, storage, and protection of extra materials shall comply with manufacturers standard requirements.

## Part 2 Products

### 2.1 Manufacturers

- A. Acceptable Manufacturer: ecoGarde Recycled Rubber Flooring which is located at 5590-46th Avenue SE, Salmon Arm, BC Canada; Toll Free Tel: 1-888-274-2490. Email: [sales@ecogarde.com](mailto:sales@ecogarde.com); Web: [www.ecoGarde.com](http://www.ecoGarde.com).
- B. Substitutions not permitted.
- C. Requests for equals will be considered in accordance with provisions of Section 01 60 00 - Product Requirements

### 2.2 Resilient / Recycled Rubber Flooring Tiles

- A. Material shall be a non-vulcanized, non-laminated tile product composed of post-consumer recycled SBR (styrene butadiene rubber) combined with low odour EPDM (ethylene propylene diene monomer) rubber granules, bound with a proprietary slow-cured MDI water-based polymer. (Essential for superior elasticity and long-term durability.)
- B. Colored toppings are made from EPDM granules. All colored toppings are approximately 1/8" (2 mm) thick with the SBR granules making up the remainder of the tile.
- C. All tiles shall be produced in a moulded form
- D. All Recycled Rubber Tiles shall be FloorScore(R) certified under the criteria developed by the Resilient Floor Covering Institute (RFCI) and certified by Scientific Certification Systems (SCS), Inc. Registration # SCS-FS-. (ecoGarde Recycled Rubber Flooring)
- E. Edge finish and product size shall be **(Enter specified selection)**
  - 1. Interlocking (24" x 24")
- F. Thickness shall be **(Enter specified selection)**
  - 1. Choose from: 1.5"
- G. Color(s) of speckle shall be **(Enter specified selection)**
  - 1. Choose from manufacturers list of colors
- H. Percentage of EPDM color speckle shall be **(Enter specified selection if custom color)**
- I. Physical properties shall conform to the requirements of the following minimum criteria:

Description	Test	Results
Sound Absorption (SAA) / Noise Reduction Coefficient (NRC)	ASTM C423	SAA 0.34 NRC 0.35
Compression Set	ASTM D395	(Method A) -2.1% (Method B) -2.2%
Breaking Load / Elongation / Tenacity	ASTM D412	Breaking Load = 91.77 lbs Elongation = 107.18% Tenacity = 174.31 lbs/sq in
Static Coefficient of Friction	ASTM D2047	Dry 0.65; Wet 0.67
Hardness Shore A Durometer	ASTM D2440	68
Taber Abrasion	ASTM D4060	Weight Loss 0.33 Grams (0.18%)
Sound Transmission Loss	ASTM E90	STC - 53
Impact Sound Transmission	ASTM E492	IIC 67 - Black IIC 58 - 20% Color
Critical Radiant Flux	ASTM E648	0.99 watts/square cm - 1.5" Black with Fire Retardant Top

Critical Radiant Flux - (15 min burn)	ASTM E648 (NY)	0.99 watts/square cm - 1.5" Black with Fire Retardant Top
Static Load (1,000 lbs)	ASTM F970	Residual Compression -0.006 In

Copies of test reports and additional product information are available upon request.

## 2.3 ACCESSORIES

- A. **Wedges & Wedge Tiles** are used around the perimeter of an area to create a transition. They can be adhered with adhesive to the edge of the tile and/or glued to the sub-surface.
  - 1. Corner wedges, designed for use on all 90° angles.
- B. **Interlocking Pins are included with every order, four per tile:**
  - 1. **1 ½" Tiles:** 3.5" long and 5/8" in diameter.
- C. **ADHESIVES**  
Provide adhesives according to manufacturer' recommendations and installation guidelines for specific substrate, and use only one of the following adhesives approved by the manufacturer:
  - 1. Chemrex CX-941, one-component urethane, volatile organic compound (VOC) compliant.
  - C. Portland based cementitious base leveller. Gypsum based not acceptable

## Part 3 Executions

### 3.1 Examination

- A. Inspect floor to be installed immediately upon arriving at job site; perform a moisture test.
- B. Do not begin installation until substrates have been properly prepared.
- C. If substrate preparation is the responsibility of another installer, notify Architect of unsatisfactory preparation before proceeding.
- D. The installation of the rubber flooring shall not begin until the work of all other trades has been completed, particularly wet and overhead trades; sheet rock work, sanding and painting.
- E. Areas to receive flooring shall be adequately lighted during all phases of the installation process.

### 3.2 Preparation

- A. Ensure that substrate is dry and clean, and shall be free of depressions, raised areas or other defects that might telegraph through installed flooring.
- B. Ensure that concrete or plywood substrate is flat and uniformly sloped. Allowable variations in substrate levels are +/- 1/8" in 10'-0" and 1/4" total maximum variation from levels shown.
- C. Concrete Substrates: The Contractor shall verify to the Owner and installer a minimum of 30 days prior to the scheduled resilient flooring installation the following substrate conditions. All substrate testing shall be documented and submitted to the Architect and Owner before commencement of the flooring installation.
  - 1. Verify that substrates are dry, free of debris, and that all curing compounds, sealers, and hardeners have properly cured.
  - 2. Remove substrate coatings and other substances that are incompatible with adhesives and that contain soap, wax, oil, or silicone, using mechanical methods recommended by manufacturer. Do not use solvents.

3. Alkalinity and Adhesion Testing: Perform tests recommended by manufacturer. Proceed with installation only after substrates pass testing.
4. Moisture Testing: Perform tests recommended by manufacturer and as follows. Proceed with installation only after substrates pass testing

### **3.3 Installation of Recycled Rubber Flooring Tiles**

- A. Do not proceed with floor surfacing installation until all applicable site work, including substrate preparation, painting, equipment installation and other relevant work by trades affecting the installation area, has been completed.
- B. Install all products in accordance with the manufacturer's Installation Guidelines.

### **3.4 Cleaning**

- A. If installers have left any adhesive residue on the rubber flooring, contact ecoGarde Recycled Rubber Flooring to determine possible solutions for removal. Do not use mineral spirits to clean adhesive of the tiles.
- B. Initial Cleaning: After completion of installation and before acceptance by Owner, perform the cleaning operations as prescribed in the manufacturer's Installation/Maintenance Guidelines.

### **3.5 Protection**

- A. Protect the installed surface from damage resulting from subsequent construction activity on the site using craft paper, plastic sheet, or other appropriate means.
- B. Touch-Up: Repair any minor damage to eliminate all evidence of repair. Remove and replace work which cannot be satisfactorily repaired.

### **3.6 Maintenance**

- A. Comply with manufacturer's instructions for proper cleaning and maintenance of the products.

### **END OF SECTION**

***These Architectural Specification Guidelines are intended for use by design and specification professionals as a template aid to specify and describe ecoGarde Recycled Rubber products as part of the written Specifications component of Construction Contract Documents.***

***The data contained in this document is accurate as of the date of publication. Updates and revisions may have been made since this date. If verification is needed that this data is still current, please contact ecoGarde Recycled Rubber Flooring at 1-888-274-2490.***